



## Product Data Sheet & General Processing Conditions

### ZOVGOV® M11G6 Acrylonitrile Butadiene Styrene (ABS) Glass Fiber

#### PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.27	1.27	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0020 in/in	0.10 - 0.20 %	D 955
<b>MECHANICAL</b>			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.2 ft-lbs/in	64 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	14000 psi	97 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	1.30 x 10 <sup>6</sup> psi	8964 MPa	D 638
Flexural Strength	19500 psi	134 MPa	D 790
Flexural Modulus	1.20 x 10 <sup>6</sup> psi	8274 MPa	D 790
<b>THERMAL</b>			
Deflection Temperature @ 264 psi (1820 kPa)	200 °F	93 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
Coefficient of Linear Thermal Expansion Flow Direction	1.5 x 10 <sup>-5</sup> /°F	2.7 x 10 <sup>-5</sup> /°C	E 831
Transverse Direction	5.4 x 10 <sup>-5</sup> /°F	9.7 x 10 <sup>-5</sup> /°C	E 831

#### PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per MOLAN Company testing.

#### GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	400 - 460 °F	204 - 238 °C
Mold Temperature	145 - 185 °F	63 - 85 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.10 %	0.10 %
Dew Point	0 °F	-18 °C

#### PROCESSING NOTES

Desiccant Type Dryer Required.