



table1-1 General Properties (ISO)

Item	Unit	Test Method	Standard, For SMT
			ME130i
			GF reinforced
Color			NAT/BLK
ISO Quality-of-the-material display:		ISO11469	>LCP-GF30<
Density	g/cm <sup>3</sup>	ISO 1183	1.61
Water absorption (23°C,24hrs,1mmt)	%	ISO 62	0.03
Tensile strength	MPa	ASTM D638	175
Tensile elongation	%	ASTM D638	2.0
Flexural strength	MPa	ISO 178	220
Flexural modulus	MPa	ISO 178	15,000
Flexural strain	%	ISO 178	2.3
Charpy notched impact strength (23°C)	kJ/m <sup>2</sup>	ISO 179/1eA	35
Temperature of deflection under load (1.8MPa)	°C	ISO 75-1,2	280
Temperature of deflection under load (0.45MPa)	°C	ISO 75-1,2	290
Electric strength (1mmt)	kV/mm	IEC 60243-1	44
Electric strength (3mmt)	kV/mm	IEC 60243-1	24
Volume resistivity	Ω·cm	IEC 60093	9 × 10 <sup>15</sup>
Volume resistivity (Our standard)	Ω·cm		-
Relative permittivity (1kHz)		IEC 60250	4.3
Relative permittivity (1MHz)		IEC 60250	3.8
Dielectric dissipation factor (1kHz)		IEC 60250	0.02
Dielectric dissipation factor (1MHz)		IEC 60250	0.03
Tracking resistance (CTI)	V	IEC 60112	125
Arc resistance	s	ASTM D495	130
Mold Shrinkage (80×80×1mmt, Flow direction, Inj. pressure 60MPa)	%	Our standard	0.02
Mold Shrinkage (80×80×1mmt, Trans-direction, Inj. pressure60MPa)	%	Our standard	0.54
Mold Shrinkage (80×80×1mmt, Flow direction, Inj. pressure79MPa)	%	Our standard	-
Mold Shrinkage (80×80×1mmt, Trans direction, Inj pressure 79MPa)	%	Our standard	-
Rockwell hardness	M(Scale)	ISO2039-2	80
Flammability		UL94	V-0

Item	Unit	Test Method	Standard, For SMT
			ME130i
			GF reinforced

All figures in the table are the typical values of the material and not the minimum values of the material specifications.