



Product Data Sheet & General Processing Conditions

ZOVGOV® M24G5FR Nylon 4/6 (PA) Glass Fiber Flame Retardant Heat Stabilized

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	25 %	25 %	
Specific Gravity	1.65	1.65	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 - 0.0050 in/in	0.30 - 0.50 %	D 955
Water Absorption, 24 hrs @ 23°C	1.800 %	1.800 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.1 ft-lbs/in	59 J/m	D 256
unnotched 1/8 in (3.2 mm) section	11.0 ft-lbs/in	587 J/m	D 4812
Tensile Strength	20000 psi	138 MPa	D 638
Tensile Elongation	2.0 - 3.0 %	2.0 - 3.0 %	D 638
Tensile Modulus	1.35 x 10 ⁶ psi	9308 MPa	D 638
Flexural Strength	31000 psi	214 MPa	D 790
Flexural Modulus	1.35 x 10 ⁶ psi	9308 MPa	D 790
Hardness Rockwell, R	120	120	D 785

ELECTRICAL

Volume Resistivity	> 1E14 ohm.cm	> 1E14 ohm.cm	D 257
--------------------	---------------	---------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	540 °F	282 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/32 in	V-0 @ 0.8 mm	D 3801
Limiting Oxygen Index**	37.0 %	37.00 %	D 2863

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per MOLAN Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	560 - 620 °F	293 - 327 °C
Mold Temperature	175 - 300 °F	79 - 149 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-40 °F	-40 °C

PROCESSING NOTES