



**Product Data Sheet &  
General Processing Conditions**

**ZOVGOV® ELC M20  
Nylon 6/6 (PA)  
ESD Protection  
Electrically Conductive**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	1.17	1.17	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0160 - 0.0250 in/in	1.60 - 2.50 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	7500 psi	52 MPa	D 638
Tensile Elongation	7.0 - 10.0 %	7.0 - 10.0 %	D 638
Tensile Modulus	0.37 x 10 <sup>6</sup> psi	2551 MPa	D 638
Flexural Strength	12000 psi	83 MPa	D 790
Flexural Modulus	0.36 x 10 <sup>6</sup> psi	2482 MPa	D 790

**ELECTRICAL**

Volume Resistivity	< 1E3 ohm.cm	< 1E3 ohm.cm	D 257
Surface Resistivity	< 1E6 ohm/sq	< 1E6 ohm/sq	D 257
Surface Resistance	< 1E5 ohm	< 1E5 ohm	ESD STM11.11
Static Decay			ESD STM11.11
MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.