



**Product Data Sheet &
General Processing Conditions**

**ZOVGOV® M26G6
Polyethylene Terephthalate (PET)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.56	1.56	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0030 in/in	0.10 - 0.30 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	12.0 ft-lbs/in	641 J/m	D 4812
Tensile Strength	22000 psi	152 MPa	D 638
Tensile Elongation	3.0 - 5.0 %	3.0 - 5.0 %	D 638
Tensile Modulus	1.60 x 10 ⁶ psi	11032 MPa	D 638
Flexural Strength	32000 psi	221 MPa	D 790
Flexural Modulus	1.40 x 10 ⁶ psi	9653 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	435 °F	224 °C	D 648
--	--------	--------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	8000 - 12000 psi	55 - 83 MPa
Melt Temperature	530 - 550 °F	277 - 288 °C
Mold Temperature	165 - 195 °F	74 - 91 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.01 %	0.01 %
Dew Point	-40 °F	-40 °C

PROCESSING NOTES

Desiccant Type Dryer Required.