



**Product Data Sheet &
General Processing Conditions**

**ZOVGOV® M23GB8
Acetal (POM)
Glass Bead**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	40 %	40 %	
Specific Gravity	1.70	1.70	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0200 in/in	1.50 - 2.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.6 ft-lbs/in	29 J/m	D 256
unnotched 1/8 in (3.2 mm) section	4.0 ft-lbs/in	214 J/m	D 4812
Tensile Strength	4900 psi	34 MPa	D 638
Tensile Elongation	7.0 - 10.0 %	7.0 - 10.0 %	D 638
Tensile Modulus	0.65 x 10 ⁶ psi	4482 MPa	D 638
Flexural Strength	10000 psi	69 MPa	D 790
Flexural Modulus	0.58 x 10 ⁶ psi	3999 MPa	D 790

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
----------------------------------------	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per MOLAN Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	360 - 425 °F	182 - 218 °C
Mold Temperature	175 - 225 °F	79 - 107 °C
Drying	2 hrs @ 250 °F	2 hrs @ 121 °C
Moisture Content	0.15 %	0.15 %
Dew Point	-25 °F	-32 °C

PROCESSING NOTES

Desiccant Type Dryer Required.